

# Château

## D

---

### Zusammensetzung

100% Perfortex® Plus.  
Schwerentflammbare Polypropylen

---

### Breite

140cm nutzbare Breite

---

### Gewicht

250g/m<sup>2</sup> ±5% (360g/lf.d.M.±5%)

---

### Scheuerfestigkeit

5 Jahre Garantie / Grad A (über 35.000),  
getestet nach Norm EN14465:2003  
(Produktgarantie erhältlich)

---

### Feuersicherung

BS EN 1021 - 1 : 2006 (Zigarettestest)  
BS EN 1021 - 2 : 2006 (Streichholztest)  
BS 7176 : 2007 Low Hazard  
BS 5852 : 2006 Section 4 Ignition Source 5  
UNI 8456 & UNI 9174 Classe 1  
NF - P - 92 - 507 M1  
DIN 4102 B1

**Bemerkung:** Schwerentflammbarkeit hängt von  
verwendetem Schaum ab.

---

### Farbabweichung

Handelsübliche Farbabweichungen vorbehalten

---

**Wichtig:** Wir behalten uns die Änderung  
technischer Spezifikationen vor.

## UK

---

### Composition

100% Perfortex® Plus.  
Flame Retardant Polypropylene

---

### Width

140cm minimum

---

### Weight

250g/m<sup>2</sup> ±5% (360g/lin.m. ±5%)

---

### Abrasion Resistance

5 year guarantee / Grade A (above 35,000)  
tested in accordance with EN 14465:2003  
(full details available)

---

### Flammability

BS EN 1021 - 1 : 2006 (cigarette)  
BS EN 1021 - 2 : 2006 (match)  
BS 7176 : 2007 Low Hazard  
BS 5852 : 2006 Section 4 Ignition Source 5  
UNI 8456 & UNI 9174 Classe 1  
NF - P - 92 - 507 M1  
DIN 4102 B1

**Note:** Flammability performance is dependent on  
foam used.

---

### Colour Matching

Batch to batch variations in shade may occur  
within commercial tolerances

---

**Note:** We reserve the right to alter technical  
specifications without notice.